

Cold Rolled Steel Strip

USAFOIL – Cold Rolled Steel Strip
BS 1449: Part 1: 1991: CS4



Form of Supply:

Tins: An assortment of sizes as shown below.

Flat Packs: An assortment of thicknesses as shown below.

Coils: Supplied to specified length or weight in the sizes shown below.

Temper: Hard Rolled 165 HV min.

Tolerances:

Thickness	Tolerance +/-
Up to an including .006"	.0006"
Over .006" Up to and including .015"	.0010"
Over .015" Up to and including .025"	.0012"

Width	Tolerance +/-
2.1/2" 4" 6"	.005"

Mechanical Properties

Tensile Strength: 540 N/mm²

Hardness: 165 HV min.

Stocked sizes – Imperial (ins)

Coils Hard Temper

x	.002	.003	.004	.005	.006	.007	.008	.009	.010	.012	.015	.020	.025
2.1/2	x	x	x	x	x	x	x	x	x	x	x	x	x
4	x	x	x	x	x	x	x		x	x	x	x	x
6	x	x	x	x	x		x		x	x	x	x	x

Tins containing 1 Length of each size

x	.002	.003	.004	.005	.010	.015
2.1/2	x	x	x	x	x	x

Flat Packs containing 1 x 12 ins Length of each size

x	.002	.003	.004	.005	.006	.008	.010	.015
4	x	x	x	x	x	x	x	x

Rugby CV21 2UW

Tel: +44 (0) 1788 542 191

Fax: +44 (0) 1788 535352

Email: sales@rug.acentasteel.com

Bolton BL4 7NN

Tel: +44 (0) 1204 576 321

Fax: +44 (0) 1204 574 511

Email: sales@man.acentasteel.com

Newport NP18 3XH

Tel: +44 (0) 1633 422 944

Fax: +44 (0) 1633 421 958

Email: sales@npt.acentasteel.com

Southampton SO40 9LX

Tel: +44 (0) 2380 871 500

Fax: +44 (0) 2380 871 150

Email: sales@stn.acentasteel.com